


S1: ARsp<0.6% @ 940 nm, AOI=45 deg
 S2 (arrow marks): HTsp>98% @ 940 nm, AOI=40-50 deg (cone), HRs>99% @ 1030 nm, AOI=45 deg



Reflectance, s, p polarization AOI=45 deg

Fig, 1

SIDE MEASURED: S1 only (grinded witness sample)

COMMENTS: Margin of measurement error: +/-0.25%