


S1: (arrow marks) HR > 99.5% @ 505-535 nm + HT > 98% @ 1000-1090 nm, AOI 45 deg. GDDr +/- 20 fs2@ 505-535 nm
 S2: AR<0.8% @ 1000-1090 nm + SCC for improved S1



PO5434 Ra i45

Fig. 1.

SIDE MEASURED: S1+S2 (good component)

COMMENTS: