


S1: HR>99.9% @ 980 – 1080nm, AOI = 5°, GDDr = -250fs<sup>2</sup> ± 100 fs<sup>2</sup> @ 980 – 1080nm  
S2: Uncoated



PO8406 Ra i8

Fig. 1.

SIDE MEASURED: S1 only (witness sample)

COMMENTS: Margin of measurement error: +/-0.25%

GDDr =  $-250\text{fs}^2 \pm 100\text{fs}^2$  @ 980 - 1080nm




Fig. 2. Measured GDD

SIDE MEASURED: S1 only (witness sample)

COMMENTS: